

INDUCTANCE CHARTS (Iron Powder Toroids)

IRON POWDER TOROIDAL CORES

MATERIAL #0	Inductance (μ h) vs. Size, Material and Number of Turns													
Turns	10	20	30	40	50	60	70	80	90	100	110	120	130	140
Size														
T-106	.19	.76	1.70	3.0	4.8	6.8	9.3	12.0	15.0	19.0	23	27	32	37
T-94	.10	.40	.90	1.7	2.7	3.8	5.2	6.8	8.6	10.0	13	15	18	21
T-80	.08	.34	.77	1.4	2.1	3.0	4.2	5.4	6.9	8.5	10	12	14	-
T-68	.07	.30	.67	1.2	1.9	2.7	3.7	4.8	6.0	7.5	-	-	-	-
T-50	.06	.26	.57	1.0	1.6	2.3	3.1	4.1	-	-	-	-	-	-
T-37	.05	.20	.44	.7	1.2	-	-	-	-	-	-	-	-	-
T-25	.04	.18	.41	-	-	-	-	-	-	-	-	-	-	-
T-20	.03	.14	-	-	-	-	-	-	-	-	-	-	-	-
T-16	.03	.12	-	-	-	-	-	-	-	-	-	-	-	-
T-12	.03	-	-	-	-	-	-	-	-	-	-	-	-	-

IRON POWDER TOROIDAL CORES

MATERIAL #1	Inductance (μ h) vs. Size, Material and Number of Turns													
Turns	10	20	30	40	50	60	70	80	90	100	110	120	130	140
Size														
T-106	3.2	13.0	29	52	81	117	159	208	263	325	393	468	549	637
T-94	1.6	6.4	14	25	40	57	78	102	130	160	194	230	270	304
T-80	1.2	4.6	10	18	28	41	56	73	93	115	139	166	194	-
T-68	1.2	4.6	10	18	28	41	56	73	93	115	139	166	194	-
T-50	1.0	4.0	9	16	25	36	49	64	-	-	-	-	-	-
T-37	.8	3.2	7	13	20	-	-	-	-	-	-	-	-	-
T-25	.7	2.8	6	-	-	-	-	-	-	-	-	-	-	-
T-20	.5	2.0	-	-	-	-	-	-	-	-	-	-	-	-
T-16	.4	1.7	-	-	-	-	-	-	-	-	-	-	-	-
T-12	.4	-	-	-	-	-	-	-	-	-	-	-	-	-

IRON POWDER TOROIDAL CORES

MATERIAL #2	Inductance (μ h) vs. Size, Material and Number of Turns													
Turns	10	20	30	40	50	60	70	80	90	100	110	120	130	140
Size														
T-106	1.4	5	12	22	34	49	66	86	109	135	163	194	228	265
T-94	.8	3	8	13	21	30	41	54	68	84	101	120	131	142
T-80	.6	2	5	9	14	20	27	35	45	55	66	79	93	-
T-68	.6	2	5	9	15	21	29	38	48	59	-	-	-	-
T-50	.5	2	2	8	12	18	24	31	-	-	-	-	-	-
T-37	.4	2	4	6	10	-	-	-	-	-	-	-	-	-
T-25	.3	1	3	-	-	-	-	-	-	-	-	-	-	-
T-20	.3	1	-	-	-	-	-	-	-	-	-	-	-	-
T-16	.2	-	-	-	-	-	-	-	-	-	-	-	-	-
T-12	.1	-	-	-	-	-	-	-	-	-	-	-	-	-